



Cactus® Double-Coated Plate Mounting Tapes

Technical Data Sheet No.TK420FL

Product Information

Cactus® Double Coated Plate Mounting Tape TK420 FL is made of compressible close-linked high resilient /medium density PE Foam with film reinforcement and acrylic solvent based pressure sensitive adhesive This model offers high performance adhesion specifically designed to firmly fix and reposition printing plates. Good resistance to heat, ink and chemical solvents, and leaves no residue after use.

Composition & Physical Properties

Adhesive System	: Acrylic Solvent	Tape Thickness	: 20 mil (0.52 ± 0.02 mm)	
Liner Material	: Crepe PP release film	Tack	: <u>Open Side</u>	: <u>Close Side</u>
		J. Dow No.	: 25	: 27
Carrier Material	: Compressible Foam w/ Film Reinforcement	Peel Adhesion	: 28.2 oz/inch	: 21.1 oz/inch
		PSTC-3	: (0.8kg / 25mm)	: (0.6kg / 25mm)
Tape Color	: Off-White	Shear Strength	: Over 24hrs with 35.3 oz loading on 1" x 1"	
		PSTC-7	: (1.0kg / 25mm x 25mm) bonding 2 stainless steel plates at 77°F (25°C)	
Liner Color	: Beige	Service Temperature	: -22°F ~ 194°F (-30°C ~ 90°C)	

Applications

- Specifically designed for Flexographic printing plate mounting - for high quality combination and process printing jobs
- With higher tenacity and Higher deflection for a better dot gain result. Good for printing on film.
- Very thin film lamination on closed side for easy repositioning and removal after use

Note : For plate mounting, apply open side of tape to printing cylinder or sleeves first, and then close side to plate. For removal, take edge of tape with both hands and peel up slowly at a 30° angle

Storage and Shelf Life

For best results, store this product at 72°F (22°C) and 50% relative humidity, use within 2 years from date of receipt.

Disclaimer and Limitation of Liability

In no event shall V. Himark USA and its employees be liable for any direct or indirect, special, incidental or consequential damage resulting from the use of this product. Therefore, it is strongly recommended that the user performs a test application first to determine the suitability of this product for the intended method of application.